

# CARLISLE WIP 200

WATER & ICE PROTECTION NON-SKID FILM SURFACE

## Self-Adhering Roofing Underlayment

### PRODUCT DESCRIPTION

Water and Ice Protection (WIP®) 200 is used as a shingle underlayment on critical roof areas like eaves, ridges, valleys, dormers and skylights. WIP membranes protect roofing structures and interior spaces from water penetration caused by wind-driven rain and ice dams.

WIP 200 is a composite membrane that consists of fiberglass-reinforced rubberized asphalt laminated to an impermeable polyethylene film layer, and provides dual-barrier moisture protection.

### INSTALLATION

#### General Information:

WIP roofing underlayments are applied when the roof deck is dry and the substrate temperature is 40°F (4.4°C) or higher. At temperatures below 40°F, nailing or priming should be used to temporarily hold the membrane in place while adhesion develops. WIP 200 is designed to be covered with the primary roofing system and should not be exposed to sunlight for more than 30 days.

*Moisture:* Substrate must be free of any moisture. If moisture is present, it may inhibit adhesion.

*New Construction:* Prepare the roof deck by removing all loose objects, dirt, dust or debris.

*Re-roofing:* Remove all old materials from the roof deck in the area to be covered with WIP roofing underlayment. Replace water-damaged sheathing and sweep roof deck thoroughly.

*Priming:* Priming is not required on clean, dry wood or metal surfaces but concrete masonry, exterior gypsum board and polyisocyanurate insulation should be primed using the appropriate primer or adhesive. Adhesives such as CCW-702 or CAV-GRIP are appropriate and required when temperatures are below 40°F.

#### Valleys, Hips & Ridges:

Cut WIP roofing underlayment into manageable lengths. Align over the center of the valley, hip or ridge. Remove release film. Press the middle of the membrane first before working toward the edges. For open valleys, cover WIP roofing underlayment with metal valley liners.

#### Eaves & Rakes:

Cut WIP roofing underlayment into 10-15' pieces. Remove 2-3' of release film and align the edge of the membrane, sticky side down, so it overhangs the drip edge by 3/8" (10 mm). Continue to remove release film and press as you move across the roof. Use a hand roller and/or hand pressure to press into place. Overlap end laps a minimum of 6". WIP roofing underlayment should reach a point 2' inside the interior wall line. Local codes may require additional courses. If additional courses are required, the top lap must be at least 3.5".

*Drip Edges:* At the rake edge, apply WIP roofing underlayment first and place drip edge on top. At the eave, apply drip edge first and place WIP roofing underlayment on top of the drip edge so that it overhangs drip edge 3/8" (10 mm).

For standard installation details, follow the WIP detail drawings. For non-standard installation instructions, contact your local Carlisle Residential representative.

### PRODUCT SPECIFICATIONS

#### PHYSICAL PROPERTIES

Surface	Black Embossed Film	
Membrane	Rubberized Asphalt—Reinforced	
<b>PRODUCT CHARACTERISTIC</b>	<b>UNITS</b>	<b>RESULTS</b>
Roll Length	feet	66
Roll Weight	lbs.	60
Coverage Per Roll	sq./ft.	200
Roll Width	inches	36
<b>TYPICAL PERFORMANCE PROPERTIES</b>	<b>TEST METHOD</b>	<b>RESULTS</b>
Thickness	ASTM D1970	55 mils
Low Temperature Flexibility	ASTM D1970	-25°F
Adhesion to Plywood at 75°F	ASTM D1970	30 lbs./ft.
Lap Seam Adhesion at 75°F	ASTM D1970	40 lbs./ft.
Sealability Around Nail	ASTM D1970	Pass
Slip Resistance	ASTM D1970	Pass
Thermal Stability	ASTM D1970	Pass
Moisture Vapor Permeance	ASTM D1970	0.03 perms
Water Absorption	ASTM D1970	0.4%
Maximum Load Machine Direction	ASTM D1970	50 lbs./in.
Maximum Load Transverse Direction	ASTM D1970	30 lbs./in.
Tear Resistance Machine Direction	ASTM D1970	85 lbs.
Tear Resistance Transverse Direction	ASTM D1970	60 lbs.
Elongation at Break Machine Direction	ASTM D1970	60%
Elongation at Break Transverse Direction	ASTM D1970	80%
<b>PACKAGING INFORMATION</b>		
Boxes (rolls) per pallet		20

### ADVANTAGES

- **Moisture and Air Barrier:** WIP 200 protects the roof structure from water seepage caused by ice dams and wind-driven rains.
- **Self Sealing:** WIP 200 membranes seal around roofing nails, staples and screws.
- **Watertight:** Used to ensure the watertightness of the primary roofing system in critical areas.
- **Self Adhering:** WIP 200 membranes bond directly to the roof substrate for fast and easy installation without the need for additional adhesives.
- **Split-Release Film:** WIP 200 features a split-release film for easier and faster installation.
- **Permanent Protection and Low Lifecycle Cost:** WIP 200 will not crack, dry out or rot and provides long-term waterproofing performance.
- **Aesthetically Pleasing:** WIP 200 is a concealed waterproofing system that will not detract from the architectural aesthetics of the primary roofing system.

## LIMITATIONS

- WIP 200 should be installed when air, roof deck and membrane temperatures are at or above 40°F (4.5°C).
- WIP 200 should not be left exposed to sunlight for more than 30 days.
- WIP 200 membrane should not be folded over the roof edge unless protected by a gutter or other flashing materials.
- The primary roof system must be ventilated to prevent excessive moisture build-up in the interior structure.
- Use caution during the installation of the membrane as it may become slippery when wet or covered with frost.
- WIP 200 should not be used under metal roofs.
- Not to be used in contact with flexible PVC material.

## APPLICABLE STANDARDS

- State of Florida Approved Product FSA# FL6782
- 2009 International Building Code™
- ICC-ES ESR# 1556
- US-UL Classified
- Meets ASTM D1970

## STORAGE

WIP 200 roofing underlayment rolls should be stored on end, under cover and in areas where the temperature is between 40° and 100°F (4.4° and 38°C). Do not double-stack pallets.

## LIMITED WARRANTY

CARLISLE COATINGS AND WATERPROOFING INCORPORATED (CARLISLE) warrants this product to be free of defects in workmanship and materials only at the time of shipment from our factory. If any CARLISLE materials prove to contain manufacturing defects that substantially affect their performance, CARLISLE will, at its option, replace the material or refund the purchase price.

This limited warranty is the only warranty extended by CARLISLE with respect to its materials. There are no other warranties, including the implied warranties of merchantability and fitness for a particular purpose. CARLISLE specifically disclaims liability for any incidental, consequential or other damages, including, but not limited to, loss of profits or damages to a structure or its contents, arising under any theory of law whatsoever.

The dollar value of CARLISLE'S liability and buyer's remedy under this limited warranty shall not exceed the purchase price of the CARLISLE material in question.

